

HyPerformance Plasma HPR400XD

The HPR400XD[®] delivers the ultimate in HyPerformance[®] mild steel cutting as well as heavy-duty stainless and aluminum capability.

Superior cut quality and consistency

HyPerformance Plasma cuts fine-feature parts with superior quality and consistency, eliminating the cost of secondary operations.

- HyDefinition[®] technology aligns and focuses the plasma arc for more powerful precision mild steel cutting up to 80 mm (3.2").
- New HDi[™] technology delivers HyDefinition cut quality on thin stainless steel from 3 to 6 mm (12 ga. to 1/4").
- Patented system technologies deliver more consistent cut quality over a longer period of time than other systems available on the market.

Maximized productivity

HyPerformance Plasma combines fast cutting speeds, rapid process cycling, quick changeovers and high reliability to maximize productivity.

Minimized operating cost

HyPerformance Plasma lowers operating costs and improves profitability.

• LongLife[®] Technology significantly increases consumable life and enables consistent HyDefinition cut quality over the longest period of time.

Unmatched reliability

Extensive testing, backed by more than five decades of experience, guarantees the Hypertherm Associates quality you can count on.

Superior cut quality on mild steel and stainless steel





Mild steel cut capacity			
Dross free*	38 mm (1-1/2")		
Production pierce	50 mm (2")		
Maximum cutting capacity	80 mm (3.2")		
Stainless steel cut capacity			
Production pierce	45 mm (1-3/4")		
Maximum pierce**	75 mm (3")		
Severance	80 mm (3.2")		
Aluminum cut capacity			
Production pierce	38 mm (1-1/2")		
Maximum cutting capacity	80 mm (3.2")		

* Feature and material type can influence dross free performance.

**Maximum pierce requires use of an autogas console and controlled motion process. See technical documentation for details.

Cut quality over life (400 A) 25 mm (1") mild steel ISO range 5: 600 Worst angle observed 3.35° to 5.33° 500 ISO range 4: Worst angle observed 400 1.68° to 3.34° Number of consumable starts Lab test - 20 second duration 300 200 100 Λ HPRXD Competitor A Competitor B (400 A) (400 A) (360 A)

Specifications

Input voltages (3-PH) and currents	VAC 200/208 220 240 380 400 440 480 600	Hz 50/60 50/60 60 50/60 50/60 50/60 50/60 60 60	Amps 262/252 238 219 138 131 120 110 88	
Output voltage	200 VDC			
Output current	400 A			
Duty cycle	100% at 40°C (104°F) at 80 kW			
Power factor	0.98 @ 80 kW output			
Maximum OCV	360 VDC			
Dimensions	118 cm (46.4") H, 88 cm (34.7") W, 126 cm (49.7") L			
Weight with torch	851 kg (1877 lbs)			
Gas supply Plasma gas Shield gas Gas pressure	O ₂ , N ₂ , F5*, H35**, Air, Ar N ₂ , O ₂ , Air, Ar 8.3 bar (120 psi) Manual gas console 8 bar (115 psi) Automatic gas console			
*F5 = 5% H, 95% N ₂ **H35 = 35% H, 65% Ar	S S			

Cut with confidence

• Hypertherm Associates is ISO 9001: 2000 registered.

- Hypertherm Associates' full-system warranty provides complete coverage for one year on the torch and leads and two years on all other system components.
- Hypertherm plasma power supplies are engineered to deliver industry leading energy efficiency and productivity with power efficiency ratings of 90% or greater and power factors up to 0.98. Extreme energy efficiency, long consumable life, and lean manufacturing lead to the use of fewer natural resources and a reduced environmental impact.

For more information, visit: www.hypertherm.com

Hypertherm, HyPerformance, HPRXD, HyDefinition, HDi and LongLife are trademarks of Hypertherm, Inc. and may be registered in the United States and/or other countries. All other trademarks are the properties of their respective owners.

Please visit www.hypertherm.com/patents for more details about Hypertherm Associates patent numbers and types.

© 9/2022 Hypertherm, Inc. Revision 5 870810



Operating data	
-----------------------	--

			Approximate		Approximate
	Current	Thickness	cutting speed	Thickness	cutting speed
Material	(amps)	(mm)	(mm/min)	(inches)	(ipm)
Mild steel	30	0.5	5355	.018	215
O2 plasma		3	1160	.135	40
O2 shield		6	665	1/4	25
O_2 plasma	80 ⁺	3	6145	.135	180
Air shield		12	1410	1/2	50
		20	545	3/4	25
O₂ plasma	130 ⁺	6	4035	1/4	150
Air shield		10	2680	3/8	110
0	000+	25	550	1	20
O2 plasma Air shield	260 [†]	10 20	4440 2170	3/8 3/4	180 90
All Siliciu		32	1135	1-1/2	30 35
O2 plasma	400 ⁺	12	4430	1/2	170
Air shield	400	25	2210	1	85
		50	795	2	30
		80	180	3	10
Stainless steel	60	3	2770	0.105	120
F5 plasma		4	2250	0.135	95
N2 shield		5 6	1955 1635	3/16 1/4	80 60
H35 and N₂ plasma*	130 ⁺	6	1835	1/4	70
N_2 shield	100'	12	875	1/4	30
		20	305	3/4	15
H35 and N₂ plasma*	260†	10	2190	3/8	90
N_2 shield	200	12	1790	1/2	65
-		20	1320	3/4	55
H35 plasma	400 ⁺	20	1100	3/4	45
N ₂ shield		50	400	2	15
		60	280	2-1/2	10
H35 and $N_{\rm 2}$ plasma*	400 ⁺	20	1810	3/4	75
N ₂ shield		50	520	2	20
		80	180	3	10
Aluminum	130	6	2215	1/4	85
H35 and N_2 plasma*		12	1455	1/2	55
N ₂ shield	000	20	815	3/4 1/2	35
N₂ plasma* Air shield	260	12 20	4290 1940	3/4	160 80
All SIIICIU		32	940	1-1/4	40
H35 and N₂ plasma*	400	12	5190	1/2	200
N_2 shield	100	50	1000	2	40
		80	210	3	10

†Consumables support up to 45° bevel capability.

* H35 and N_2 mixed plasma gas requires the use of an autogas console.

The operating data chart does not list all processes available for the HPR400XD. Please contact Hypertherm Associatesfor more information.

As 100% Associate owners, we are all focused on delivering a superior customer experience. www.hyperthermassociates.com/ownership

Environmental stewardship is one of Hypertherm Associates' core values. www.hyperthermassociates.com/environment

100% Associate-owned

